Industrial, Aviation, Medical Applications

Data Sheet - RMB 283 Rotational Molding Grade PVDF

Physical Properties	Specification	Value	Notes
Specific Gravity	ASTM D792	1.78	
Melt Flow Rate	ASTM D1238	>8 g/10 min.	230°C, 2.16 kg
Mechanical Properties			
Tensile at Yield	ASTM D638	3600 PSI	
Tensile at Break	ASTM D638	3600 PSI	
Elongation at Break	ASTM D638	20%	
Flexural Modulus	ASTM D790	145 KSI	
Izod Impact (notched)	ASTM D256	2.3 FT-LBS/IN	0.15" thick
Izod Impact (unnotched)	ASTM D256	No Break	0.15" thick
Thermal Properties			
Melt Point	ASTM D3418	160°C	DSC Peak
Glass Transition	ASTM D5023	-37°C	Tan Δ Peak
Coefficient of Linear			
Thermal Expansion			
0°C - 40°C	ASTM E831	1.49E-04	mm/mm/°C
100°C - 140°C	ASTM E831	3.64E-04	mm/mm/°C

Properties data based on rotationally molded samples in the as molded condition.

Characteristics: RMB 283 is a PVDF co-polymer, specifically formulated for rotational molding applications such as fluid tanks. Excellent physical properties, low moisture absorption and excellent chemical resistance combined with ease of processing make RMB 283 a cost effective alternative. Conforms to FDA No. 21 CFR 177.2510

The information set forth herein is furnished free of charge and is based on technical data that RMB Products believes to be reliable. It is intended for use by persons having technical skill, at their own discretion and risk. The handling precaution information contained herein is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Because conditions of product use are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any material, evaluation of any compound under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate under or a recommendation to infringe any patents.

Rev. B Sept. 12, 2012